

Ordernumber : 2621
Date of order : 07-07-2005
Your reference : Brief 06-07-2005

Leotex
Slibbroek 39
5081 Hilvarenbeek

Description : upholstery fabric

SAMPLE
05262101

Your reference : **CAPRI**

Date of receipt : 07-07-2005
Date analyses : Week 28

Sampling by : third party
Place analyses : Servaco

Resistance to domestic washing 30° C ISO 5077/ EN ISO 26330 8A

Method : twwhw30

washing temperature 30° C, detergent ECE flatdrying and conditioning 20° C - 65 % RH

dimensional change	
warp direction	-1.0 %
weft direction	-1.4 %
change in colour	4-5 grade on the grey scale

Resistance to dry cleaning ISO 5077

Method : twwcr solvent : perchloroethylene conditioned

dimensional change	
warp direction	-0.9 %
weft direction	-1.0 %
change in colour	5 grade on the grey scale

M. Gaillez
Section Head Textiles

Dr. Nicholas Van Landuyt
Administrator